

TEST REPORT

Technical Report: (5220)182-0655

Page 1 of 7
July 15, 2020



Report Number
(5220)182-0655



**BUREAU
VERITAS**

TEST REPORT

TO : SAMSONITE ASIA LTD
25/F, TOWER 2, THE GATEWAY,
HARBOUR CITY
25 CANTON ROAD, TSIM SHA TSUI
KOWLOON,
HONG KONG

ATTN : WINNIE LAM

LAB NO.: (5220)182-0655
FORM NO.: /
DATE IN: Jul 02, 2020
DATE OUT: Jul 15, 2020
DEPARTMENT: /
NO. OF WORKING DAYS: 9
PAGE 2 OF 7

OVERALL RATING

PASS	X
FAIL	_____
DATA	_____

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	#3 GOLDSUN 210D, WASHABLE W/R, DW30 0.7% OWF ON PU 1 TIME COATING, HEAT TRANSFER PRINT	Style Description:	/
Color:	/	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
Finishing:	/	Age Group:	/
SKU:	/		

Product Category	/
Test Requested	ANTIFUNGAL ACTIVITY ASSESSMENT AGAR PLATE, ASPERGILLUS (AATCC 30)
Previous Report No.	/

Submitted Fiber Content	/
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
ANTIFUNGAL ACTIVITY ASSESSMENT AGAR PLATE, ASPERGILLUS	X			

BUREAU VERITAS HONG KONG LTD.



YVONNE LUK
SENIOR MANAGER - SOFTLINES

TEST PROPERTY

TEST RESULTS

REQUIREMENTS

Method Summary :

The anti-fungal activity was evaluated using the AATCC Test Method 30 Antifungal Activity Assessment on Textile Materials, Test III. The following organism was used for this test: *Aspergillus niger* ATCC strain 6275.

Pre-wet test specimen was placed on agar surface. The fungal inoculum was then distributed evenly over the specimen by means of a sterile pipette. Observation of any growth covering the specimen is recorded.

Result :

Test Component (A):

Face side of black with grey and light grey checked textile

Percentage of surface area covered with the growth of <i>Aspergillus niger</i>	
Antifungal-treated sample	
No Growth	
Comment	
PASS	
Test photo: see exhibit img52201820655-M3001	

NOTE :

- The percentage of surface area not covered with fungus cannot be construed as a quantitative evaluation of antifungal activity.

Client's Acceptance Criteria: **No Growth**

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
----------------------	---------------------	---------------------

Method Summary :

The anti-fungal activity was evaluated using the AATCC Test Method 30 Antifungal Activity Assessment on Textile Materials, Test III. The following organism was used for this test: *Aspergillus niger* ATCC strain 6275.

Pre-wet test specimen was placed on agar surface. The fungal inoculum was then distributed evenly over the specimen by means of a sterile pipette. Observation of any growth covering the specimen is recorded.

Result :

Test Component (B):

Face side of black with grey and light grey checked textile

Percentage of surface area covered with the growth of <i>Aspergillus niger</i>	
Untreated sample	
Macroscopic growth :	60 - 100 %
Comment	
DATA	
Test photo: see exhibit img52201820655-M3002	

NOTE :

- The percentage of surface area not covered with fungus cannot be construed as a quantitative evaluation of antifungal activity.

img52201820655-M3001:



img52201820655-M3002:

